

Technical Data Sheet



W V C O

Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service,
innovation, and integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

CANADIAN WILLAMETTE

325 Edworthy Way
New Westminster, BC V3L 5GA
Tel 800.663.4298

TAPEL WILLAMETTE TD. S.A

Av. Estero La Posada 3625
Coronel, Chile
Tel. 011.56.42.2 928.100
www.tapel.cl

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

CU-100-S Synthetic Patch

Two-Component Polyurethane Wood Filler

DESCRIPTION

CU-100-S Synthetic Patch is a two-component ambient temperature curable polyurethane (6:1 by ratio) resin system. It is designed for faster sanding and planing. The resin is solvent-free and composed of 100% non-volatile organic compounds (zero VOC). It is designed and APA approved to fill and up-grade plywood panels, laminated beams, mouldings, door blanks and other wood products. The two components are mixed and applied using WVCO's dispensing and metering equipment.

WHERE TO USE

- Plywood Panels
- Laminated Beams, Mouldings, Door Blanks
- Industrial Mill Environments

FEATURES AND BENEFITS

- Designed for Faster Sanding and Planing
- Metering Reduces Waste
- Zero VOC

PACKAGING

5 gallon pails
Drums
Totes

SHELF LIFE

3 months from date of manufacture when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F. DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Density – lbs / gallon	Part A	10.8
	Part B	10.3
pH		7
Viscosity, cps, ASTM D 4878	Part A	3500
	Part B	200
Mix Ratio – Part A:B by volume		6:1
Set Time at 77°F (25°C) in seconds		25 to 90
Color		Available in many colors

APPLICATION

CU-100-S is metered through Willamette Valley Company's metering equipment and dispensed through a static mix tube. Application should be on wood no hotter than 190°F with moisture content no greater than 8%-12%. CU-100-S is ready for sanding 1 hour after application. For more information regarding application, please contact your Willamette Valley Company representative.

ADVANTAGES

Since the resin is mixed in the static mix tube as it is dispensed, only the amount needed is utilized, substantially reducing unnecessary waste.

The polyurethane components are always mixed in the same ratio. This ensures consistency in the final product's properties.

Because both polyurethane components are contained, exposure to any hazardous materials is reduced. Also, being contained reduces the polyurethane's exposure to moisture, enhancing the quality of the polyurethane system.

The combined savings in disposal of hazardous waste, material cost, improved productivity, quality and the time saved due to ratio control yields tremendous overall savings.

The B-Side (iso-side) contains methylene diphenyl diisocyanate (MDI). It has extremely low vapor pressure, and therefore is very unlikely to become airborne.

NOTES

This product is supplied to the customer in a ready to use form. Any addition of water or other materials will result in degradation of the product performance.

HEALTH AND SAFETY

Willamette Valley Company recommends reading and becoming familiar with the Material Safety Data Sheet before using.

CONTACT INFORMATION

Please see the side bar on this and the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

EASTERN DIVISION

6662 Marbut Road
Lithonia, GA 30058-5234
Tel. 888. 878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors, MN 55616
Tel. 218.834.3922

PERFORMANCE COATINGS

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.polyquik.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
Po Box 188
Malad City, Idaho 83252
Tel 208.766.2206

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.

