

Technical Data Sheet



The Willamette Valley
Company LLC

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

NETHERLANDS BRANCH

Willamette Valley Co. B. V.
Spurkt 1B
5804 AR Venray
The Netherlands
Tel. 011.31.478.220020

E-851 Epoxy - Thin

Two-component epoxy used to fill wood defects

DESCRIPTION

E-851 is a two-component polyamine hardened epoxy used for the repair of defects in wood. Used in the wood products industry; it can be applied by meter or cartridge and spread with a putty knife on an assembly line operation. The thinner viscosity reduces mounding which reduces the amount of epoxy used, which in turn requires less sanding. The thinner viscosity also enables the epoxy to flow into narrow/thin defects very well. The product sets up in about 90 seconds, depending on temperature of the wood and the volume of the defect. Once cured, E-851 Epoxy can be easily sanded, planed, cut, stained, painted and drilled. E-851 Epoxy is also free from the irritating odors of unsaturated polyester and mercaptan cured epoxies.

WHERE TO USE

- Dimensional Lumber
- Laminated Beams
- Wood Flooring
- Fir and Cedar Siding
- Unrouted and Routed Defects in Plywood
- Molding, Furniture

FEATURES AND BENEFITS

- Can be Sanded, Stained, Painted & UV Cure Coated
- Zero VOC – 100% Solids
- Thin Viscosity: Use Less Epoxy
- Less Mounding: Less Sanding
- Can be Applied in Hot or Cold Temperature Wood
- Outstanding Adhesion to Wood
- Great Moisture Resistance
- Fully Cured Epoxy is Crack and Shrink Resistant

PACKAGING

Cartridges
5-gallon pails (18.93 L)
55-gallon drums (208.2 L)

SHELF LIFE

12 months when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F (7.2°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Solids		100%
Density – lbs./gallon (kg/L)	Part A	10 (1.20)
	Part B	12 (1.44)
Consistency		Thick Fluid
Viscosity – centipoise at 77°F (25°C)	Part A	35,000 cps
	Part B	35,000 – 45,000 cps
Pot Life: at 77°F (25°C) in 100 mls or ½ cup (varies with quantity and temperature)		90 seconds
Color (other colors available upon request)		Black
Hardness – Shore “D” (on fully cured material)		65

CURE TIME

Remember that epoxy is exothermic when curing, so the larger the mass the faster it will cure. Avoid filling larger voids in one pour as it may become extremely hot as it cures. Allow epoxy to cure for 30 minutes before sanding. Epoxy will fully cure within 24 hours.

APPLICATION

E-851 can be applied by mechanical or hand methods:

Mechanical – Use a Willamette Valley Company metering system. Please contact your Willamette Valley Company Representative for information on using a metering system.

Cartridges -

1. E-851 can be dispensed from cartridges with a side-by-side manual or pneumatic gun. A 24-30+ -element nozzle with a 10 mm diameter is required to achieve a sufficient mix.
2. Use a 1-to-1 manual dispenser.
3. Remove the retaining nut and caps from the cartridge.
4. Keep the cartridge upright during assembly.
5. Place mix tube on top of the cartridge and secure by hand tightening the retaining nut.
6. Point cartridge upward and load into applicator gun.
7. While pointing cartridge upward, trigger handle to remove any air trapped in cartridges.
8. Point cartridge over waste container and dispense an initial amount of material (e.g. approximately 20mL).
9. Flood defect but avoid overfilling. Use a flexible blade putty knife to spread the epoxy further reducing the amount of epoxy used and the amount of post-cure sanding needed.

NOTE: Application by cartridge must be performed continuously. Stopping before the cartridge is completely dispensed will result in the material setting up in the mix tube. Partially used cartridges may be reused by placing a new mix-tube on top of the cartridge.

Hand Method – By hand, mix the two-components at a 1:1 ratio by volume. After hand mixing, apply using a flexible blade putty knife to spread the epoxy.

ADDITIONAL FEATURES AND BENEFITS

The E-851 Epoxy can be used to repair numerous types of wood products such as:

- ✓ Upgrading dimensional lumber and plywood
- ✓ Filling Defects in Laminated Beams
- ✓ Correcting imperfections in fir and cedar siding
- ✓ Repairing unrouted plywood defects up to 1.5" (3.81 cm)
- ✓ Repairing routed plywood defects up to 2.25" (5.72 cm)
- ✓ Fixing Defects in Molding and Furniture

Part "A" and Part "B" of E-851 Epoxy have similar viscosities and therefore accommodate easy mixing. In addition E-851 has been formulated with specific thixotropic agents which allows it to be easily mixed and applied on hot or cold temperature wood.

NOTES

As it is true with most epoxies, prolonged exposure to direct sunlight will cause the cured epoxy to yellow and degrade over time. Avoid applications of E-851 Epoxy in areas where direct exposure to sunlight is expected.

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

CLEAN-UP

Use soap and water before the material solidifies.

CONTACT INFORMATION

Please see the side bar on the front page for the Division nearest to your location.

**THE WILLAMETTE VALLEY
COMPANY LLC**
www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE PRODUCTS

990 Owen Loop North
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQUICK.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

990 Owen Loop North
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

CANADIAN DIVISION SURREY BRANCH

19081- 27th Avenue
Surrey BC V3S 5T1
Tel 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
990 Owen Loop North
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2.928.100
www.tapel.cl



W07-R&D-TDS-066

Rev. 01

Revision Date: October 2020

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.