Technical

Data Sheet



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service, innovation, and integrity

WESTERN DIVISION

660 McKinley Street Eugene OR 97402 Tel. 800.333.9826

MIDWEST DIVISION

1549 Hwy 2 Two Harbors MN 55616 Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive Pineville LA 71361 Tel. 800 444 9826

EASTERN DIVISION

6662 Marbut Road Lithonia GA 30058 Tel. 888.878.9826

EPly-Sealer RC Cherry

Sealer for Engineered Wood

DESCRIPTION

The Willamette Valley Company has formulated EPly-Sealer RC Cherry, a high quality styrene acrylic, high performance wax, face sealer specifically designed to meet the needs of the plywood and engineered wood industries. It is a surface treatment that minimizes checking, splitting and moisture damage which cause the dimensional instability of wood substrates. EPly-Sealer RC has excellent water repellency and less stickiness than regular wax-based sealers. It is an economical and environmentally safe product.

WHERE TO USE

- Engineered Wood Products: LVL, OSB
- Plywood
- Other Wood Product Plants

FEATURES AND BENEFITS

- Excellent Water Repellency and Moisture Protection
- Ease of Application
- Environmentally Sound
- Long Lasting Moisture Barrier

PACKAGING

1-Gallon (3.78 L) Pails 5-Gallon (18.93 L) Pails

Drums

Totes

Tankers

SHELF LIFE

3 months when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F (7.2°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Viscosity at 78°F (25.5°C) (centipoise)	145
Solids (percent by weight)	28%
Wt. / Gal. lbs/gallon (kg/liter)	8.36 (1.00)
Color – Cherry	

APPLICATION

Apply one coat of EPIy-Sealer RC Cherry by Roll Coater at a film thickness of 1-3 mils. If a higher application rate is applied to obtain a higher performance, a blocking concern needs to be considered. Check with your Willamette Valley Company representative for directions and recommendations.

CLEAN-UP

EPly-Sealer RC Cherry can be washed off with water prior to the film drying. If the sealer has dried, scrubbing with hot water and detergent is advised.

NOTES

This product is supplied to the customer in a ready to use form. Any addition of water will result in degradation of the product performance.

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on the right and the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

1075 Arrowsmith Street PO Box 2280 Eugene, OR 97402 Tel 541.484.9621 www.POLYQUIK.com www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street Eugene, OR 97402 Tel 541.484.2368 www.pre-tec.com

SUBSIDIARIES

CANADIAN WILLAMETTE

19081- 27th Avenue Surrey BC V3S 5T1 Tel. 800.663.4298

ECLECTIC PRODUCTS INC.

Corporate Office 1075 Arrowsmith Street Eugene, OR 97402 Tel 541.284.4667 www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy PO Box188 Malad City, Idaho 83252 Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625 Parque Industrial Coronel Coronel, Chile Tel 011.56.41.928.100 www.tapel.cl

