

Technical Data Sheet



W V C O

Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service,
innovation, and integrity

CENTRALIA DIVISION

1830 Central Blvd.

Centralia WA 98531

Tel 866.924.9826

CANADIAN WILLAMETTE

19081- 27th Avenue

Surrey BC V3S 5T1

Tel. 800.663.4298

MEDFORD BRANCH

736 Mason Way

Medford OR 97501-1354

Tel: 800.888.9826

TAPEL WILLAMETTE LTD. S.A.

Av Estero la Posada 3625

Parque Industrial Coronel

Coronel Chile

Tel. 011.56.41.2928.100

www.tapel.cl

BATES WILLAMETTE, LLC

P.O. Box 1328

2242 MacArthur Dr.

Orange TX 77630

Tel. 409.883.0384

FIR BARK B-80

Plastic Reinforcing Series

DESCRIPTION

Fir Bark B-80 is used as an extender filler in plastics. The fir bark reinforces the impact strength of plastic and improves various molding and finishing properties of plastic.

WHERE TO USE

- In Plastic Manufacturing

FEATURES AND BENEFITS

- High Fiber Strength
- Low Moisture and Ash Content
- Improves Stability
- Consistently Uniform from Bag to Bag
- Increases Strength and Impact Resistance
- Forty Year of Proven Performance

PACKAGING

Bags - 45 Pound

SHELF LIFE

12 months when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Max Retained on 50 Mesh (Reynolds Air Swept Particle Size Analyzer)	1.00%
Max Retained on 100 Mesh (Reynolds Air Swept Particle Size Analyzer)	8.00%
Moisture Content +/-2% (Computrac Max 5000)	5%
Product Content	Douglas Fir Bark
Bulk Density	17 lbs / Cubic Foot
Color	Reddish Brown

NOTES

This product is supplied to the customer in a ready to use form. Any additions or alterations may result in degradation of the product performance.

CONTACT INFORMATION

Please see the side bar for the Sales Office nearest to your location.

HEALTH AND SAFETY

Before handling, you should become familiar with the Material Safety Data Sheet (MSDS) regarding the risks and safe use of this product. To obtain an MSDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

PERFORMANCE COATINGS

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQuik.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILLING & GRAIN

430 W 445 N
P.O. Box 188
Malad ID 83252
Tel. 208.766.2206



Revision Date: May 2012

For revisions or latest version please contact:
800 333 9826 ext 5525 or 07julien@wilvaco.com

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.