

Technical Data Sheet



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

WESTERN DIVISION

660 McKinley Street

Eugene OR 97402

Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road

Lithonia GA 30058

Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2

Two Harbors MN 55616

Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive

Pineville LA 71361

Tel. 800 444 9826

Wil-Jet A

Ink Jet Ink

DESCRIPTION

Willamette Valley Company has formulated an acetone-based ink-jet ink specifically designed to meet the needs of the OSB, plywood and lumber industries.

WHERE TO USE

- OSB panels
- Plywood panels
- Lumber

FEATURES AND BENEFITS

- Bold legible printing
- Available in a variety of colors

PACKAGING

5-gallon pails (18.9 L)
Drums

SHELF LIFE

12 months when stored **unopened**.

STORAGE

Store this product in a well ventilated place. Keep away from sources of ignition. Keep cool.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Wt./gal. (Kg/Lt)	6.75 (0.81)
Color	black, red & blue

APPLICATION

Please contact your Willamette Valley Company representative for determining the suitability of Wil-Jet A in your application system.

CLEAN-UP

Wil-Jet A can be cleaned with acetone prior to the ink drying. If the coating has dried it may respond to acetone clean-up but may need to be mechanically removed.

NOTES

This product is supplied to the customer in a ready-to-use form. Do not dilute the product as that will compromise the strength of the ink and could lead to poor quality printing.

When changing over to Wil-Jet A ink it is recommended that the application system be thoroughly cleaned and free of the previous ink. Cleaning should include the printing heads, filters, intermediate tanks and tubing. It is recommended to change the filter as part of the pre-start-up preparation.

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.polyquik.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

CANADIAN DIVISION SURREY BRANCH

19081- 27th Avenue
Surrey BC V3S 5T1
Tel. 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2 928.100
www.tapel.cl



DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.

W07-R&D-TDS-028

REV 00

Revision Date: April 2016