

Technical Data Sheet



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

Wil-Seal 2012 Red

Composite Panel Edge Sealer

DESCRIPTION

Wil-Seal 2012 Red is formulated to seal and protect the edges of composite panel substrates from water-induced swelling. Coverage rate is dependent upon the level of performance desired, but 8-10 wet mils is recommended for protection against water penetration.

WHERE TO USE

- OSB
- Particleboard
- MDF
- OSL

FEATURES AND BENEFITS

- Excellent Moisture Protection
- Increases Wood Shelf Life
- Fills Voids to Seal Effectively
- Long Lasting Moisture Barrier

PACKAGING

Tote – 330-gal. (1249 L)
Bulk

SHELF LIFE

3 months from delivery when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment between 40 - 80°F (4.4-26.6°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Percent Solids	25%
Viscosity, centipoise @77 F (25°C)	600
Weight / Gallon (lbs./gallon) Specific Gravity (kg / L)	8.33 1.0
pH	9.3
Color	Red

APPLICATION

Wil-Seal 2012 Red is designed for spray applications. For other types of application methods check with your Willamette Valley Company representative for directions and recommendation for use.

CLEAN-UP

Clean equipment before the paint dries completely. If the paint has dried, hot water, detergent and scrubbing will be required.

NOTES

This product is supplied to the customer in a ready-to-use form. Any addition of water or other liquid to change viscosity may result in degradation of the product performance.

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS please call 800 333 9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.polyquik.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

CANADIAN DIVISION SURREY BRANCH

19081- 27th Avenue
Surrey BC V3S 5T1
Tel 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO. Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2 928.100
www.tapel.cl

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.



W07-R&D-TDS-074

R00

Revision Date: March 2017