

Technical Data Sheet



The Willamette Valley
Company LLC

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

POLYQuik® Gasket A-20

Shore A Gasket Material

DESCRIPTION

POLYQuik® Gasket A-20 is a soft, low viscosity, self-leveling urethane material designed for gasket applications.

WHERE TO USE

- Industrial Casting
- Soft Gasket Applications

FEATURES AND BENEFITS

- Fast Cure
- Very Soft and Flexible
- Low Viscosity
- Self-leveling
- 1:1 Ratio by Volume –easy application

PACKAGING

5-gallon Pail Set (37.8 L)
50-gal. Drum Set (378 L)

SHELF LIFE

12 months when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment between 60-95°F (15-35°C).

TYPICAL PROPERTIES

Unmixed Components		Resin	Iso
Viscosity, cP		900	2500
Density, lbs/gal (kg/L)		8.8 (1.054)	9.1 (1.09)
Color		Black	Pale Yellow
Mix Ratio	By Weight	1	1
	By Volume	1	1

Mixed Material	
Gel Time –minutes at 77°F (25°C)	1.5
Shore A hardness Cured 18-24 hours at 70°F (21°C)	17-22
Color	Black

APPLICATION

METER DISPENSED

PROCESSING

1. Use WVCO meter or equivalent at a 1 to 1 ratio by volume. For metered applications, contact Willamette Valley Company Precision Technologies Division (PRE-TEC) for equipment recommendations or more details.
2. Condition RESIN and ISO to 70°F (21°C) or other desired controlled temperature $\geq 70^{\circ}\text{F}$ (21°C) for 24 hours before using.
3. Mechanically mix RESIN for 30-60 minutes. Use mix blades that are 1/3 the diameter of the container.
4. Dispense a small portion of POLYQuik® Gasket A-20 to ensure dispensing equipment is working correctly before dispensing into application area and/or after pail or drum changeover.
5. WVCO recommends using a 13-mm diameter mix tube with at least 32 mix elements or equivalent (contact Willamette Valley Company for more details or approved equivalents).
6. Inspect and verify POLYQuik® Gasket A-20 color/mixing is uniform and the material cures uniformly in 1 hour at 70°F (21 °C).

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS, please call (800) 333-9826 or send an email to: msds@wilvaco.com.

THE WILLAMETTE VALLEY COMPANY LLC

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

990 Owen Loop North
PO Box 2280
Eugene OR 97402
Tel 541.484.9621
www.POLYQUIK.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

990 Owen Loop North
Eugene OR 97402
Tel 541.484.2368
www.pre-tec.com

CANADIAN DIVISION SURREY BRANCH

19081- 27th Avenue
Surrey BC V3S 5T1
Tel 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
990 Owen Loop North
Eugene OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO Box 188
Malad City Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel Chile
Tel 011.56.41.2.928.100
www.tapel.cl



DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.

W07-R&D-TDS-102

Rev 01

Revision Date: August 2020