



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service,
innovation, and integrity

POLYQuik® HPU-1229

Fire Retardant Elastomeric Coating

DESCRIPTION

POLYQuik® HPU-1229 is a two-component, aromatic, sprayable, hybrid polyurea elastomeric coating. It is used as an elastic waterproof protective coating for construction and industrial applications. It is specifically formulated for applications where fire retardancy is required. POLYQuik® HPU-1229 passes ASTM E84 Class A requirements for flame spread and smoke index, and has been tested according to other fire standards.

WHERE TO USE

- **Fire Retardant Coating**—for construction and industrial
- **Waterproofing**—parts or assemblies
- **Abrasion Resistant Coating**—for industrial parts
- **Protective Coating**—for metal, concrete and wood

FEATURES AND BENEFITS

- **ASTM E84 Class A**—slows fire spread, low smoke
- **ASTM E648 Class 1**—passes flooring standard
- **Two-Component Cure**—sets within seconds
- **Impact and Abrasion Resistance**—protects substrate

PACKAGING

5-gal. pails (18.9 L)
50-gal. drums (189 L)

COLORS

White, Red

YIELD

5-gallon pail set (10 gal total) = 1.34 ft³
50-gallon drum set (100 gal total) = 13.36 ft³

Sprayed Yield*: 26 ft² per gal or 3.8 gal per 100 ft²
at 60 mil DFT (0.63 m² per L at 1.5 mm DFT)

*assumes 100% transfer

SHELF LIFE

1 year when properly stored.

STORAGE

Store and ship this product in a clean, dry, low-humidity, shaded or covered environment at 60 to 90°F (15 to 32°C).

TECHNICAL INFORMATION

Typical Properties

VOC , lbs/gal (g/L), ASTM D 2369	0
Viscosity , cps, ASTM D 4878, Resin / Iso	2800 /450
Service temperature , ° F (° C)	-26 to 190 (-32 to 88)
Gel time , sec	5
Tack-free time , sec	10
Recoat time , hours	24
Tensile ,* psi (MPa), ASTM D 412	2500 (17.2)
Elongation ,* %, ASTM D 412	110
Hardness ,* Shore D, ASTM D2240	57D
Tear ,* pli (kN/m), ASTM D 1938	100 (17)
Tear, (Die C)* pli (kN/m), ASTM D 624	380 (66)
Abrasion Resistance* mg lost, H-18 wheel, 1kg, 1k cycles, ASTM D 4060	232
Fire Retardancy**, Flame Spread Index/Smoke Index ASTM E84, 40 mil film	FSI 25, SI 400
Fire Retardancy**, Critical Radiant Flux kW/m ² , ASTM E648, 40 mil film	CRF 0.59

*Properties achieved using specific dispensing equipment

** Other testing protocols have been checked –

Contact WVCO for more information

Processing Parameters

Ratio by volume	1 to 1
Application temp , ° F (° C)	40 to 110 (4.4 to 43)
Recommended thick. , mils (mm)	20 to 125 (0.5 to 3.0)
Meter equipment	Heated Plural Component (30 Mesh Y-Strainer)
Gun requirement	Impingement spray gun (40 Mesh Screens)
Spray pressure , psi (MPa)	2,000 to 3,000 (13.6 to 20.4)
Spray temperature , primary heaters and hose, °F (° C)	140 to 180 (60 to 82)

APPLICATION

SURFACE PREPARATION

WOOD

1. Store wood in a covered, dry location, and protect surface from damage and contamination.
2. For a completely uniform appearance in the finished product, fill all voids, spaces or damaged areas prior to coating. Repair or fill all areas with suitable wood filler. Contact WVCO representative for filler options and technical recommendations. Remove any excess filler by sanding until level with the surrounding area.
3. Priming may be required. Prime with POLYQuik® PolyPrime or other suitable primer. Contact WVCO representative for primer options and technical recommendations. Refer to primer technical data sheet for application and cure time information.
4. Ensure wood surface is smooth and dry prior to applying POLYQuik® HPU-1229. Surface should be sanded with 36-120 grit or have equivalent smoothness, and have less than 10% surface moisture. Humidity greater than 85% and surface moisture greater than 10% will create blisters between the coating and the wood surface.
5. Apply HPU-1229 in two 10-20 mil (0.3-0.5 mm) coats in crosshatch pattern and allow to cure 2-3 minutes. Repeat this application until desired thickness is achieved.

CONCRETE

1. Priming is recommended; prime with POLYQuik® PolyPrime or other suitable primer. Contact WVCO representative for primer options and technical recommendations. Refer to primer technical data sheet for application and cure time information.
2. The surface being coated must be fully cured (28 days minimum), structurally sound (200 psi or greater tensile strength according to ASTM D 7234), clean (ASTM D 4258), and dry (less than 5% surface moisture, ASTM E1907 and D4263).
3. The surface must have low moisture vapor transmission (less than 3 lb/24 hr/1000 ft², RMA Test Method).
4. Do not apply over concrete if vapor barrier is not present or unknown.
5. Profile surface according to ICRI Guide 03732 to a minimum of CSP 3 by abrasive blasting or hydroblasting. Remove contaminants before blasting.
6. Fill all voids and cracks between 0.06-0.50" (1.5-12.5 mm) with suitable filler. Contact WVCO representative for filler options and technical recommendations.

STEEL & OTHER METALS

1. Steel and other metal surfaces must be cleaned before blasting according to SSPC-SP1. Remove any sharp edges, weld splatters and other surface imperfections.
2. Blast according to SSPC-SP10 / NACE No. 2 Near White standard (0.003" (0.08 mm) profile).
3. Test the surface for non-visible soluble salt contamination according to NACE 6G186. If necessary treat the surface with CHLOR*RID or equivalent chloride remover until less than 3 mg/cm² is detected.
4. PRIMING STEEL OR OTHER METALS – Apply POLYQuik® Epoxy Primer or PolyPrime only if metal surface temperature is 5° F (3°C) above the dew point to avoid application over damp surface. Refer to primer technical data sheet for application and cure time information. Contact your WVCO representative for approval before using other primers or if immersion service is intended.

5. For aluminum and galvanized metals, contact your WVCO representative for additional information.

PROCESSING

1. Precondition material to at least 70°F (21°C) for 24 hours. Secure an air driven mixer with 3 folding blades in the center bung hole of the drum. Air driven mixer blade configuration: 8" blade - bottom, 6" blade - middle, and 6" blade - top. Ensure the mixer is spinning clockwise at a speed adequate enough to thoroughly mix the resin. Mix for 30 minutes before spraying. Repeat above mixing instructions after every 4 hours of operation. Avoid mixing for more than 30 minutes as air may become entrapped in the resin. Mixers are available through WVCO Precision Technologies.
2. HPU-1229 must be sprayed with a high pressure plural-component proportioner. Contact WVCO representative for plural component proportioner recommendations and configurations. Proportioner should be able to heat resin and iso to 150-180°F (65-82°C).
3. Proportioner must generate a minimum spray pressure of 2,000 psi (13.8 MPa), maintain a stable pressure during spray and keep minimal pressure differential between resin and iso – no more than 300 psi – during application.
4. Contact WVCO representative for high and low output application equipment. Equivalent applicator setups from other manufacturers are available. CAUTION: APPLICATOR OUTPUT MUST NOT EXCEED 75% OF METER OUTPUT.

APPLICATION

1. When priming, prime according to Surface Preparation guidelines. Refer to primer technical data sheet for application and cure time information.
2. Avoid blisters and poor adhesion by not applying coating when the humidity is above 85%. Apply the coating when the substrate temperature is stable or dropping. Minimize out-gassing and pinholes on concrete with primers, and with multiple thin applications of coating (10 mils or less per pass).
3. Clean surface of contaminants (i.e. dust, dirt). Surface may be blown with dry compressed air or use a tack cloth.
4. Spray HPU-1229 in a consistent sweeping pattern, 15-20 mils per pass as a general guideline and maintaining a consistent distance from the substrate. ALWAYS START AND STOP SPRAYING OFF TARGET TO AVOID BLISTERING.
5. Apply an optional texture coat over the surface to create a uniform appearance.
6. Recoat without surface preparation is possible within 24 hours of application at 70°F cure. After 24 hours abrade the surface and clean with acetone or POLYQuik® Cleaner, and recoat within 1 hour.
7. Proper application is the responsibility of the user. Field visits by a WVCO representative are for the purpose of making technical recommendations only, and are not for supervising or providing quality control on the jobsite.

CLEANING & MAINTENANCE

- Use POLYQuik® Cleaner to clean applicators and parts after every use. Do not immerse the entire applicator in Cleaner.
- CLEAN Y-STRAINERS REGULARLY.
- Contact WVCO representative for pump flushing and long term storage stability recommendations.

HEALTH AND SAFETY

Before handling, you should become familiar with the Material Safety Data Sheet (MSDS) regarding the risks and safe use of this product. To obtain an MSDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVCO DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

DIVISIONS

WESTERN DIVISION

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQUIK.com
www.SPIKEFAST.com

EASTERN DIVISION

6662 Marbut Road
Lithonia, GA 30058
Tel 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors, MN 55616
Tel 218.834.3922

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SOUTHERN DIVISION

100 Dixie Mae Drive
PO Box 4450
Pineville, Louisiana 71361
Tel 318.640.5077

SUBSIDIARIES

CANADIAN WILLAMETTE

19081- 27th Avenue
Surrey BC V3S 5T1
Tel. 800.663.4298

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
Po Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625 Parque
Industrial Coronel Coronel, Chile
Tel 011.56.41.2.928.100
www.tapel.cl



Revision Date: Sept 2014