

Technical Data Sheet



W V C O

The Willamette Valley
Company LLC

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

FastPatch Crack Filler

DESCRIPTION

FastPatch Crack Filler is a rapid setting, two-part polyurethane designed for concrete repair. Designed for damaged concrete surfaces with large and small cracks, FastPatch Crack Filler can extend the life of the concrete. Its combination of fast set, high strength and low viscosity make it ideal for areas which must be brought to level.

WHERE TO USE

- Concrete – small and large cracks
- Joints - broken corners and edges
- Low temperature application – cures on cold surfaces

FEATURES AND BENEFITS

- Excellent concrete adhesion without primer
- Low viscosity – penetrates and levels
- Fast Setting – cures in minutes
- High shore D hardness

PACKAGING

600 mL cartridge
250 mL universal cartridge

COLORS

Gray

STORAGE

Store and ship this product in a clean, dry, low-humidity, shaded or covered environment at 60 to 90° F (15 to 32° C).

SHELF LIFE

1 year when properly stored

TECHNICAL INFORMATION

Typical Properties

VOC , %, ASTM D 2369	3.4
Viscosity , cps, ASTM D 7234, mixed	1000
Service Temperature , °F (°C)	-40 to 185 (-40 to 85)
Gel time , min. at 70° F (21° C)	1-2
Set Time , min	1-3 (temperature dependent)
Adhesion to Concrete , psi, (MPa), ASTM D7234, unprimed	≥ 1000 (6.9) Substrate failure
Ultimate Hardness , Shore D, ASTM D2240	75-80
Tensile Strength , psi, ASTM D412	4700

Processing Parameters

Mix Ratio by Volume , Resin : Iso	1:1
Application Equipment	Pneumatic, battery-powered electric, or hand operated cartridge dispenser with 10 X 30 static mix tube

APPLICATION

SURFACE PREPARATION

CONCRETE

1. The concrete surface being repaired must be fully cured, structurally sound, clean and dry.
2. Concrete joints must be free of all foreign matter, including old joint filler, asphalt, tar, paint, wax, rust, membranes and curing/parting compounds. Contaminants present can result in poor adhesion. Apply product only if surface temperature is 5° F (3° C) above dew point to avoid application over damp surface.
3. Remove any surface contaminants before applying FastPatch CF by grinding, sweeping, wire brushing or another appropriate method.
4. FastPatch CF is intended for crack and spall repair. It is not for joint filling or over areas which may expand or contract significantly. Movement of the underlying concrete may cause cracking along the sides of the repair, or reflective cracks in a topcoat. Joints must be allowed freedom of movement; use FastPatch EJC family of joint compounds as directed.
5. FastPatch CF is not recommended for use on bare ground, dirt, grass or other non-structural surfaces. Contact your WVCO representative for recommendations, and before using on surfaces intended for immersion service.

PROCESSING

1. If possible, precondition material to 70°F (21°C) before use.
2. Do not dilute either resin or iso with any solvents. Contact WVCO for additional mixing recommendations.

APPLICATION

1. Before application, protect adjacent surfaces with tape or other kinds of protective barriers. Corner and edge repairs require damming the areas with tape to keep the material in place during cure.
2. Cracks in concrete may be deeper than they appear. The low viscosity of FastPatch CF may allow material to fall through the surface, leaving gaps or holes visible. These gaps may be repaired by pushing sand into the gap and dispensing FastPatch CF over it. Contact your WVCO representative for filler recommendations.
3. Avoid very shallow or wide applications. It is recommended that the crack to be filled is at least twice as deep as it is wide for optimal adhesion and performance.
4. Saw cuts and cracks wider than 1/8" (3 mm) may be filled with backer rod of appropriate diameter before dispensing FastPatch CF.
5. When recoating, abrade the surface of the previously installed FastPatch CF to ensure adhesion.
6. Contact your WVCO representative for recommendations on other repair scenarios.

CARTRIDGE APPLICATION

1. Use a 1-to-1 dispenser, pneumatic, hand operated, or battery-powered electric preferred (maximum of 40 psi for pneumatic).
2. Remove the retaining nut and caps from the cartridge.
3. Keep the cartridge upright during assembly.
4. Place mix tube on cartridge nozzle, use retaining nut if necessary.
5. Keep cartridge upright and load into applicator gun.
6. Begin dispensing with cartridge upright to remove any trapped air.
7. Dispense initial material (20-40mL) outside the repair area and discard.
8. Dispense Remaining material onto the repair area. Avoid triggering on and off to keep the materials on ratio. If adjacent areas are uneven, fill to the lower height. Do not overfill. Change mix tubes if dispensing stops for 20 seconds.
9. Avoid mixing newly dispensed material with partially cured material, as this may cause discoloration.
10. Topping sand may be added to refusal while the material is still tacky. After material sets, excess may be sanded to give a smooth finish for topcoat.

HEALTH AND SAFETY

Before handling, you should become familiar with the Material Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an MSDS please call 800-333-9826 or send an email to: sds@wilvaco.com

THE WILLAMETTE VALLEY COMPANY LLC

www.wilvaco.com
info@wilvaco.com

DIVISIONS

WESTERN DIVISION

990 Owen Loop North
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQUICK.com
www.SPIKEFAST.com

EASTERN DIVISION

6662 Marbut Road
Lithonia, GA 30058
Tel 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors, MN 55616
Tel 218.834.3922

PRECISION TECHNOLOGIES DIVISION

990 Owen Loop North
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SOUTHERN DIVISION

100 Dixie Mae Drive
PO Box 4450
Pineville, Louisiana 71361
Tel 318.640.5077

CANADIAN DIVISION

SURREY BRANCH
19081 - 27th Avenue
Surrey BC V3S 5T1
Tel. 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
990 Owen Loop North
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
Po Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2.928.100
www.tapel.cl



DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVCO DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

W07-R&D-TDS-115

REV 01

Revision Date: August 2020