



Willamette Valley Company

www.wilvaco.com

www.polyquik.com

www.fastpatchsystems.com

800.333.9826

fastpatch@wilvaco.com

Partnering through service,
innovation, and integrity

FastPatch DPR

Distressed Pavement Repair

DESCRIPTION

FastPatch DPR is an easy to apply durable pavement reinstatement material. It is supplied in bulk containers for rapid deployment or kits with everything included for ease-of-use. It is a polymer binder based on a blend of recycled and renewable materials designed to be installed in clean, dry and sound areas. There are color options of Gray, Black, and Tan; topping sand can be applied to provide a textured surface. It can be applied in warm conditions, or in cooler conditions with the aid of FastPatch Kicker accelerator, to form a fast return-to-service reinstatement material. DPR has good adhesion to concrete and asphalt and can be used to permanently repair a wide variety of pavement damage.

WHERE TO USE

- **Roadways** – spalls, wheel paths, approaches/departures
- **Parking Lots** – holes, walkways, broken areas
- **Micro-Trenches** – roadways, joints
- **Warehouses** – floors, spalls, loading areas
- **Sidewalks** – trip hazards, walkways

FEATURES AND BENEFITS

- **Easy-to-Apply** – mix, pour, & finish in minutes
- **Lasting Repair** – excellent adhesion & absorbs impact
- **Open to Traffic Quickly** – reduce traffic interruptions
- **Recycled & Renewable Materials** – sustainable sources
- **Odorless** – 100% solids & suitable for indoor applications
- **Freeze-Thaw Resistant** – long term repair for colder climates

KIT PACKAGING (aggregate included)

FastPatch DPR Kit, 3-gallon (11-Liter), 0.4 cubic ft
FastPatch DPR Kit, 1.5-gal (5-liter), 0.2 cubic ft

BULK PACKAGING

5-gallon (19-Liter) Pail
50-Gallon (190-Liter) Drum
250-Gallon (946-Liter) Tote

COLORS

Gray, Black or Tan (bulk only)

SHELF LIFE

1 year when properly stored.

STORAGE

Store and ship this product in clean, dry, low-humidity, and shaded or covered environments between 50 and 90°F (10-32°C)

TYPICAL PROPERTIES

	Result	ASTM
Solids Content	100%, SCAQMD compliant	-
Hardness	85-90 Shore A	C661
Ultimate Elongation	90%	D412
Ultimate Tensile Strength	≥1,300 psi	D412
Concrete Adhesion	≥200 psi; Primarily substrate failure	D7234
Compressive Strength (mixed with aggregate)	1,200 psi	C579 method B 24hr ambient cure
Compressive Strength (mixed with aggregate)	1,500 psi	C579 method B 7 day ambient cure
Mix Ratio by Volume	1 : 1 polymer A : B 1 : 2 polymer : aggregate*	-
Recommended Application Thickness	≥1/4" (0.635 cm) 4" (10cm) max per lift for bulk	-
Recommended Repair Area for Kits	≤16ft ² (1.49m ²)	-
Application Temp. Range	40 to 105°F (4 to 40°C) **	-

*may vary depending on application method.

1 gallon DPR bulk with 2 gallons glass yields approx. 2.6 gallons of mixed material

**application may be possible outside the recommended range. Contact your WVCO rep. for more information

APPLICATION INSTRUCTIONS

For instructions on how to handle and apply FastPatch DPR from kits please refer to [FastPatch DPR Kit Instructions](#). Details on how to successfully repair distressed pavement with the DPR Kits can be found in the [FastPatch DPR Kit Application Guidelines](#). For applications with WVCO/Pre-Tec metering equipment and/or FastPatch Aggregate Mixer (example: bulk applications for trench repairs), refer to [FastPatch DPR Bulk Application Guidelines](#). Training for the WVCO/Pre-Tec meter can be provided. If you have specific questions related to your dispensing equipment, please contact your WVCO representative or customer support.

ESTIMATED RETURN TO SERVICE

Standard DPR Kits:

Temperature	Working-Time, minutes [with (1) optional Kicker]	Return-To-Service, hours [with (1) optional Kicker]
110°F (43°C)	7 [3]	0.5 [<0.5]
70°F (21°C)	20 [10]	1 [0.75]
40°F (10°C)	60 [40]	3-4 [2-3]

DPR Bulk Applied at Recommended Aggregate Ratio*:

Temperature	Working-Time, minutes [with (1) optional Kicker] {with (2) optional kickers}	Return-To-Service, hours [with (1) optional Kicker] {with (2) optional Kickers}
110°F (43°C)	25 [15] {10}	1 [0.75] {<0.5}
70°F (21°C)	30 [20] {15}	1.5 [1] {0.75}
40°F (4°C)	90 [75] {50}	4 [3-4] {3}

*estimates based on 1 gallon DPR bulk mixed with 2 gallons glass (both conditioned to specified temp.) and cured at ambient (75°F, 21°C) conditions.

ESTIMATED YIELD*

*DPR Yield-volumes are based on mixtures with aggregate at recommended ratio.

	Yield
Per 1 gallon (3.8 liter) bulk DPR material	2.5 gallons (9.5 L) 0.33 cubic foot
FastPatch DPR Small Kit	1.25 gallons (4.25 L) 0.17 cubic foot
FastPatch DPR Standard Kit	2.5 gallons (9.5 L) 0.33 cubic foot
FastPatch DPR Standard Kit with optional gravel addition	3.0 gallons (11.4 L) 0.4 cubic foot

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS, please call 800-333-9826 or send an email to: msds@wilvaco.com.

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVCO DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

WILLAMETTE VALLEY COMPANY
www.wilvaco.com
info@wilvaco.com

DIVISIONS WESTERN

DIVISION

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQUIK.com
www.SPIKEFAST.com

EASTERN DIVISION

6662 Marbut Road
Lithonia, GA 30058
Tel 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors, MN 55616
Tel 218.834.3922

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SOUTHERN DIVISION

100 Dixie Mae Drive
PO Box 4450
Pineville, Louisiana 71361
Tel 318.640.5077

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2.928.100
www.tapel.cl



W07-R&D-TDS-033
REV 01
Revision Date: November 2016