



Willamette Valley Company

[www.wilvaco.com](http://www.wilvaco.com)

[www.polyquik.com](http://www.polyquik.com)

800.333.9826

Partnering through service,  
innovation, and integrity

# POLYQuik® PolyPrime LV

Low-Viscosity, Bonding Agent for Concrete Repairs

## DESCRIPTION

POLYQuik® PolyPrime LV is a 2-component, low-viscosity urethane primer for concrete repairs. PolyPrime LV is designed for easy application at a wide range of temperatures and fast recoat times with FastPatch repair products. PolyPrime LV can be brush/roller applied and will ensure your repair area has an excellent bond.

## SUBSTRATES

- Concrete
- FastPatch Concrete Repair Products
- POLYQuik® Joint Sealants

## FEATURES AND BENEFITS

- Rapid Cure - 20 minute recoat time at 70°F (21°C)
- Low Viscosity - easy to brush, great surface wetting
- Adhesion Promoter - ensures excellent bond line
- 1:1 Ratio by Volume
- No equipment required
- Applies easily from 40-100°F (4-38°C)

## PACKAGING

20-oz (600-mL) Cartridge  
½-gallon (1.9-liter) Kit  
2-gallon (7.6-liter) Kit

## SHELF LIFE

1 year when properly stored.

## STORAGE

Store and ship this product in clean, dry, low-humidity, shaded or covered environment between 50 and 90°F (10-32°C)

## TYPICAL PROPERTIES

	Result	ASTM Method
Solids Content	96.4%	D2369
Working Time, minutes, cup 70°F (21°C)	20	-
Concrete Adhesion, psi (MPa)	1,000 (6.9)	D4541
Steel Adhesion, psi (MPa)	1,000 (6.9)	D4541
Minimum Recoat Time, minutes, concrete substrate 70°F (21°C)	20	-
Minimum Recoat Time, minutes, concrete substrate 40°F (4°C)	30	-
Mix Ratio (by volume)	1:1	-

---

## APPLICATION INSTRUCTIONS

---

For instructions on how to handle and apply PolyPrime LV from cartridges, please refer to [POLYQuik® Cartridge Instructions](#). For brush/roller applications, please refer to: [POLYQuik® Primers Installation Guidelines](#). PolyPrime LV is not recommended for high pressure spray or meter dispensed applications. Contact your WVC representative for more information or help selecting the best primer for your application.

For use in conjunction with FastPatch repair products, please refer to: [POLYQuik® Concrete Spall and Crack Repair Guidelines](#)

---

## RECOAT TIMES AND COVERAGE

---

Because PolyPrime LV has excellent wetting and soaks into the concrete surface, tack free time is not a good indicator for recoat time. WVC R&D has measured the optimum recoat time with adhesion strength testing according to ASTM D4541. Below are optimum results:

Ambient & Substrate Temperature	Minimum Recoat Time
95°F (35°C)	10 minutes
70°F (21°C)	20 minutes
40°F (4°C)	30 minutes

Estimated coverage is based on a single coat of brush-applied PolyPrime LV on concrete substrate as observed during actual repairs in the field. Below is a Coverage Chart:

Packaging	Coverage Area ft <sup>2</sup> (m <sup>2</sup> )
20-oz (600-mL) cart.	30 (2.8)
½-gallon (1.9-liter) kit	96 (8.9)
1-gallon (3.8-liter) of mixed material	192 (18)
2-gallon (7.2-liter) kit	384 (35)

---

## HEALTH AND SAFETY

---

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS, please call 800-333-9826 or send an email to: [msds@wilvaco.com](mailto:msds@wilvaco.com)

DISCLAIMER OF WARRANTY  
TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVC DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

**WILLAMETTE VALLEY COMPANY**  
[www.wilvaco.com](http://www.wilvaco.com)  
[info@wilvaco.com](mailto:info@wilvaco.com)

### DIVISIONS

#### WESTERN DIVISION

1075 Arrowsmith Street  
PO Box 2280  
Eugene, OR 97402  
Tel 541.484.9621  
[www.POLYQUIK.com](http://www.POLYQUIK.com)  
[www.SPIKEFAST.com](http://www.SPIKEFAST.com)

#### EASTERN DIVISION

6662 Marbut Road  
Lithonia, GA 30058  
Tel 888.878.9826

#### MIDWEST DIVISION

1549 Hwy 2  
Two Harbors, MN 55616  
Tel 218.834.3922

#### PRECISION TECHNOLOGIES DIVISION

675 McKinley Street  
Eugene, OR 97402  
Tel 541.484.2368  
[www.pre-tec.com](http://www.pre-tec.com)

#### SOUTHERN DIVISION

100 Dixie Mae Drive  
PO Box 4450  
Pineville, Louisiana 71361  
Tel 318.640.5077

### SUBSIDIARIES

#### ECLECTIC PRODUCTS INC.

Corporate Office  
1075 Arrowsmith Street  
Eugene, OR 97402  
Tel 541.284.4667  
[www.eclecticproducts.com](http://www.eclecticproducts.com)

#### IDAHO MILL & GRAIN

445 North 430 West Hwy  
PO Box 188  
Malad City, Idaho 83252  
Tel 208.766.2206

#### TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625  
Parque Industrial Coronel  
Coronel, Chile  
Tel 011.56.41.2.928.100  
[www.tapel.cl](http://www.tapel.cl)



W07-R&D-TDS-021  
REV 00  
Revision Date: March 2016