Technical

Data Sheet



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service, innovation, and integrity

WESTERN DIVISION

660 McKinley Street Eugene OR 97402 Tel. 800.333.9826

CANADIAN WILLAMETTE

325 Edworthy Way New Westminster, BC V3L 5GA Tel 800.663.4298

TAPEL WILLAMETTE TD. S.A

Av. Estero La Posada 3625 Coronel, Chile Tel. 011.56.42.2 928.100 www.tapel.cl

SOUTHERN DIVISION

100 Dixie Mae Drive Pineville LA 71361 Tel. 800 444 9826

U-100 Synthetic Patch

Two-Component Polyurethane Wood Filler

DESCRIPTION

U-100 Synthetic Patch is a two-component urethane system that has found extensive use in upgrading plywood panels, filling voids in laminated beams, mouldings, floor blanks and other wood products. It works well under medium density overlay. U-100 is designed so the set time can be adjusted to suit the customer's needs.

WHERE TO USE

- Plywood Panels
- Laminated Beams, Mouldings, Door Blanks
- Industrial Mill Environments

FEATURES AND BENEFITS

- APA Approved quality assurance
- Metering Reduces Waste
- Zero VOC safer work environment

PACKAGING

5-gallon pails

Drums

Totes

SHELF LIFE

3 months from date of manufacture when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F (7.2°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Density – lbs / gallon (kg / L)	Part A Resin	12.9 (1.55)
	Part B ISO	10.3 (1.2)
Viscosity, cps, ASTM D 4878	Part A Resin	2624
	Part B ISO	200
Mix Ratio – Part A:B by volume		6:1
Set Time at 77°F (25°C) in seconds Custom set times available upon request		25 to 75
Color		Available in many colors

APPLICATION

U-100 is metered through Willamette Valley Company's metering equipment and dispensed through a static mix tube. Application should be on wood no hotter than 190° F (87.7°C) with moisture content no greater than 8-12%. U-100 is ready for sanding 1 hour after application. Contact your Willamette Valley Company representative for information about metering equipment.

ADVANTAGES

Since the resin is mixed in the static mix tube as it is dispensed, only the amount needed is utilized, substantially reducing unnecessary waste.

The polyurethane components are always mixed in the same ratio. This ensures consistency in the final product's properties.

Because both polyurethane components are contained, exposure to the uncured product is reduced. Also, being contained reduces the polyurethane's exposure to moisture, enhancing the quality of the product.

The combined savings in disposal of hazardous waste, material cost, improved productivity, quality and the time saved due to ratio control yields tremendous overall savings.

The Willamette Valley Company also offers an excellent Full Service Warranty.

NOTES

This product is supplied to the customer in a ready to use form. Any addition of water or other materials will result in degradation of the product performance.

HEALTH AND SAFETY

Before handling, you should become familiar with the Material Safety Data Sheet (MSDS) regarding the risks and safe use of this product. To obtain an MSDS please call 800 333 9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on this and the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com info@wilvaco.com

OTHER DIVISIONS

EASTERN DIVISION

6662 Marbut Road Lithonia, GA 30058-5234 Tel. 888. 878.9826

MIDWEST DIVISION

1549 Hwy 2 Two Harbors, MN 55616 Tel. 218.834.3922

PERFORMANCE COATINGS

1075 Arrowsmith Street PO Box 2280 Eugene, OR 97402 Tel 541.484.9621 www.polyquik.com www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street Eugene, OR 97402 Tel 541.484.2368 www.pre-tec.com

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office 1075 Arrowsmith Street Eugene, OR 97402 Tel 541.284.4667 www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy Po Box188 Malad City, Idaho 83252 Tel 208.766.2206



