

Technical Data Sheet



W V C O

Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service,
innovation, and integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

Wil-Pro SP-1127 Regular White

Interior/Exterior Primer – High Hiding

DESCRIPTION

Willamette Valley Company has formulated Wil-Pro SP-1127 as a high hiding primer for MDF and pine moulding. Wil-Pro SP-1127 is a premium water-based moulding primer that is custom formulated for use in an industrial mill production line. Wil-Pro SP-1127 provides a clean white finish that is ideal for accepting interior/exterior paints.

WHERE TO USE

- MDF and Pine Moulding
- Industrial Mill Environments

FEATURES AND BENEFITS

- High Hiding Primer
- Accepts Any Interior/Exterior Latex Paint
- Strong Adhesive Bond to Latex Paint
- Clean White Color Attracts Customers

PACKAGING

Drums
Totes

SHELF LIFE

6 to 9 months when properly stored.

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F(7.2°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

pH	8.5
Percent Solids	61%
Viscosity in seconds, #2 Zahn cup @77 F (25°C)	29
Weight / Gallon, lbs./gallon (Kg / L)	12.67 (1.52)
Spread Rate @3.5 wet mils, ft ² / gal (m ² / L)	458 (11.2)
Spread Rate @ 4 wet mils, ft ² / gal (m ² / L)	400 (9.8)
Color	White

APPLICATION

Apply Wil-Pro SP-1127 by airless spray, at a wet film thickness of 3.5 - 8 mils. For other types of application methods check with your Willamette Valley Company representative for directions and recommendation for use.

Primer coating can be dried with conventional air, forced hot air or IR.

CLEAN-UP

Clean equipment before paint dries completely. If the paint has dried, hot water, detergent and scrubbing will be required.

NOTES

This product is supplied to the customer in a ready to use form. Any addition of water to reduce viscosity may result in degradation of the product performance.

HEALTH AND SAFETY

Before handling, you should become familiar with the Material Safety Data Sheet (MSDS) regarding the risks and safe use of this product. To obtain an MSDS please call 800 333 9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com
info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.polyquik.com
www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SUBSIDIARIES

CANADIAN WILLAMETTE

19081- 27th Avenue
Surrey BC V3S 5T1
Tel. 800.663.4298

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
Po Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2 928.100
www.tapel.cl

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.



Revision: May 2012